CRUMB RUBBER DIRECT

Tire-Derived Fuel (TDF)

Data sheet · RE-TDF · sales@crumbrubberdirect.com

Chip size	Nominal ≤1 in / 1 in Minus
Steel	Production target <1%
Moisture	≤2.0%
HHV	Typical 14,000-15,500 BTU/lb (ASTM D5865)
Sulfur	Typical <2.0% (ASTM D4239)
Chlorine	Typical <0.30% (ASTM D4208)
Packaging	Supersacks with or without pallets, or bulk on request

typical values are industry-standard or representative production data. Confirmed per lot on your written quote. No prices on this sheet — request a quote.

Packaging: supersacks / bulk bags, with or without pallets. Typical net weight ~2,000 lb per sack (confirmed on quote). Gaylords or loose bulk on request.

FOB Central Ohio. Material is not represented as meeting any particular ASTM, DOT, playground or turf requirement unless separately documented.

© 2026 Crumb Rubber Direct · crumbrubberdirect.com